

SALES SPECIFICATION

FOAM GRADE: **P200-38Y1**

COLOR: YELLOW

EFFECTIVE: 12-04-00

SUPERSEDES: 03-01-00

TEST ITEM	UNIT	RANGE	TEST METHOD
DENSITY	PCF	1.85-2.05	ASTM 3574
I.F.D. @ 4" THICK			
- 25% DEFLECTION	LBS.	32.0-42.0	ASTM 3574
- 65% DEFLECTION	LBS.	57.6 MIN.	ASTM 3574
SUPPORT FACTOR	RATIO	1.80 MIN.	
RECOVERY	%		
HYSTERESIS LOSS	%	N/A	
COMPRESSION FORCE DEFLECTION	LBS.	N/A	
CONSTANT DEFLECTION COMPRESSION SET			
- 90% DEFLECTION	%	10.0 MAX.	ASTM 3574
- 50% DEFLECTION	%	5.0 MAX.	ASTM 3574
STEAM AUTOCLAVE AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	ASTM 3574
- C. F. D. LOSS @ 50%	%		
DRY HEAT AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	
- C. F. D. LOSS @ 50%	%		
AIR FLOW	CFM	2.0 MIN.	ASTM 1564
RESILIENCE (BALL TEST)	%	45.0 MIN.	ASTM 3574
TENSION TEST			
- TENSILE STRENGTH	PSI	10.0 MIN.	ASTM 3574
- ULTIMATE ELONGATION GRIP SEPARATION	%	125 MIN.	ASTM 3574
TEAR RESISTANCE	PLI	1.00 MIN.	ASTM 3574
STATIC FATIGUE 75%			
- I. F. D. LOSS @ 25%	%	N/A	ASTM 3574
- THICKNESS LOSS @ 75% COMPRESSION	%	N/A	ASTM 3574

FOAMEX MAKES NO WARRANTY EXPRESS OR IMPLIED, EXCEPT THAT SUCH POLYURETHANE FOAM PRODUCTS MEET OR EXCEEDS THE CRITERIA OUTLINED ABOVE AT THE TIME OF SHIPMENT. FOAMEX MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS OF THE GOODS FOR ANY PARTICULAR PURPOSE. USER SHALL DETERMINE THE APPROPRIATENESS OF THESE MATERIALS FOR INTENDED APPLICATIONS, AND ASSUMES TOTAL LIABILITY REGARDING DAMAGE OR LOSS ARISING FROM THE USE OF THIS PRODUCT.

