

Bob's Foam Factory, Inc.
4055 Pestana Place
Fremont, CA 94538
Phone (510) 657-2420
Fax (510) 657-2423
Toll Free (800)-270-2420

Foam Grade FV250-34Y

_(MEETS TEST STANDARD: ASTM-D-3574, CAL – 117)

3220 F SPEC

| | |
|--------------------------------------|-------------|
| DENSITY, lbs / cu. ft. | 1.75 – 1.85 |
| ILD, lbs. / 50 sq. in. 25% (4") | 30 – 36 |
| Tear Strength, psi | 225 min |
| Tensile Strength, psi | 17 min |
| Elongation, % | 225 – 350 |
| Resilience, % | 40 min |
| Compression Sets, 90%, 22 hrs, 158 F | 10% max |
| Color | WHITE |

